



INDUSTRIAL AIR FILTRATION

AFFINITY™
FILTER MEDIA

PPS BAGHOUSE FILTER BAGS

FIT FOR MULTIPLE ENVIRONMENTS

Works well in varied baghouse conditions where **continuous operating temperatures are up to 375°F (190°C)**.

KEY BENEFITS



GOOD CHEMICAL RESISTANCE

Won't deteriorate when exposed to various chemicals and industrial solvents.



HIGH-TEMPERATURE RESISTANCE

Supports applications with operating temperatures up to 375°F (190°C).



FLAME-RESISTANT

Does not support melting, dripping or combustion.



FIT FOR MULTIPLE ENVIRONMENTS

Highly suitable for numerous filtration environments.

FEATURES

- Highly resistant to chemicals such as acids, alkaline, organic solvents, and corrosion.
- Flame and hydrolysis resistant.
- Combine with P84® for **Tandem™ filter bag** or Basalt in our **Meteor™ filter bag**.
- Fits any baghouse to specification.
- Quality assurance under the strictest protocols to ASTM standards.
- 100% virgin premium fibers.
- Extremely stable.



OPTIONS

- Fire Retardant
- Water-Repellent Treatment
- Oil Repellent Treatment
- PTFE Finish
- E-PTFE Membrane
- Scrim Supported
- Singed
- Wear Strips
- Non-Woven Cuff
- Woven Cuff
- NFPA Wire



APPLICATIONS

- Mining
- Cement
- Metals
- Oil & Gas
- Power Plants
- Minerals

AFFINITY™
FILTER MEDIA

FABRIC PROPERTIES

	100% PPS	PPS + P84 (Tandem™)	PPS + Basalt (Meteor™)
Abrasion Resistance	Very Good	Very Good	Very Good
Acid Resistance	Excellent	Very Good	Good
Alkali Resistance	Excellent	Good	Good
Oxidation Resistance	Moderate	Moderate	Moderate
Operating Temperature	375°F (190°C)	375°F (190°C)	375°F (190°C)
Investment	\$\$\$	\$\$\$\$	\$\$\$\$

Contact Albarrie's Technical Sales Expert for all your options

PRODUCT GALLERY



Disclaimer: Information provided by Albarrie on this sales sheet ("Sheet") is for general information purposes only. All information on the Sheet is provided in good faith, however Albarrie makes no representation or warranty of any kind, express or implied, regarding the accuracy, adequacy, validity, reliability, availability or completeness of any information on the Sheet. Products may not work as advertised or perform differently based on application, operating conditions, and depend on chemical, thermal, and humidity and other factors.

